



Colorant for SBR Type LB

[Feature]

- Pigments are dispersed in a vehicle with good compatibility with rubber.
- The product is in sheet form.
- Excellent dispersion, diffusion, and color stability for various types of rubber (NBR, SBR, etc.).
- Your desired hue can be achieved by mixing the base colors.



[Characteristic]

Product Name	Color Index	Concentration (%)	Color
Resino Yellow GL-6-F (LB)	Disazo Yellow (P.Y.14)	50	
Resino Yellow 3GR-55-C (LB)	Disazo Yellow (P.Y.13)	52	
Resino Yellow 2R-B (LB)	Disazo Yellow (P.Y.14、P.Y.55)	35	
Resino Yellow 5GS-B (LB)	Disazo Yellow (P.Y.83)	40	
Resino Lemon Yellow 50% (LB)	Iron Oxide (P.Y.42)	50	
Resino Brown 205 (LB)	Iron Oxide (P.R.101)	50	
Resino Brown 400 (LB)	Iron Oxide (P.R.101)	29	
Resino Orange G-A (LB)	Pyrazolone Orange (P.O.13)	50	
Resino Orange RA-A (LB)	Disazo Orange (P.O.16)	52	
Resino Red K (LB)	Lake Red (P.R.48:1)	47	
Resino Red BX (LB)	Lake Red (P.R.48:2)	45	
Resino Carmine FB-D (LB)	Naphthol Carmine (P.R.5)	62	
Resino Red 72-A (LB)	Naphthol Red (P.R.170)	36	
Resino Blue KP-25 (LB)	Phthalocyanine Blue (P.BI.15:3)	13	
Resino Blue RT-SA-A (LB)	Phthalocyanine Blue (P.BI.15:2)	43	
Resino Blue RT-6-A (LB)	Phthalocyanine Blue (P.BI.15:2)	56	
Ultramarine 1500 50% (LB)	Ultramarine Blue (P.BI.29)	50	
Resino Green GBA (LB)	Phthalocyanine Green (P.G.7)	41	
Resino Black F-4 (LB)	Carbon Black (P.Bk.7)	35	

[Note]

Please mix the required amount with a small amount of rubber to check the hue before use.

[Note]

Data on this page can't be used for specification purposes.
Please evaluate the sufficient performance of the sample under the conditions of use.



RESINO COLOR INDUSTRY CO., LTD.

Head Office TEL : +81-6-6301-0636

Sales Office TEL : +81-3-3634-1746

<http://www.resinocolor.co.jp/>