



# Base Color for Polyvinyl Chloride

## Feature

- Pigments are dispersed in a vehicle with good compatibility with PVC resin.
- Products are in granular form.
- Excellent dispersibility, diffusibility, and color stability in both soft and rigid PVC.
- Your desired color tone can be achieved by mixing the base colors.



## Characteristic

Product Name	Color Index	Concentration (%)	Packing (kg)	Color
Yellow NSB-127	Azo condensation Yellow (P.Y.128)	5	15	Yellow
Yellow NSB-128	Azo condensation Yellow (P.Y.128)	40	5	Yellow
Yellow NSB-134	Azo condensation Yellow (P.Y.95)	45	5	Yellow
Yellow NSB-139	Isoindolinone (P.Y.110)	40	5	Orange
Yellow NSB-1/10-139-D	Isoindolinone (P.Y.110)	4	10	Yellow
Yellow NSB-156	Disazo Yellow (P.Y.83)	40	10	Yellow
Yellow NSB-236	Zinc Ferrite (P.Y.119)	60	15	Brown
Yellow NSB-1/10-236-D	Zinc Ferrite (P.Y.119)	6	15	Brown
Brown NSB-215	Benzimidazolone (P.Br.25)	40	5	Brown
Brown NSB-216	Iron Oxide (P.R.101)	60	15	Brown
Brown NSB-1/10-216-D	Iron Oxide (P.R.101)	6	15	Brown
Red NSB-35	Lake Red (P.R.48:2)	40	10	Red
Red NSB-40	Naphthol Carmine (P.R.150)	40	10	Red
Red NSB-46	Quinacrydone Magenta (P.R.122)	40	10	Red
Red NSB-66	Quinacrydone Red (P.V.19)	5	15	Red
Red NSB-67	Quinacrydone Red (P.V.19)	40	5	Red
Red NSB-83	Azo condensation Scarlet (P.R.166)	5	10	Red

Product Name	Color Index	Concentration(%)	Packing (kg)	Color
Red NSB-84	Azo condensation Scarlet (P.R.166)	40	5	
Red NSB-86	Diketo Pyrrolo Pyrrole (P.R.254)	45	5	
Blue NSB-320	Phthalocyanine Blue (P.Bl.15:3)	40	10	
Blue NSB-1/10-320-D	Phthalocyanine Blue (P.Bl.15:3)	4	15	
Blue NSB-323	Phthalocyanine Blue (P.Bl.15:2)	42	10	
Blue NSB-363	Phthalocyanine Blue (P.Bl.15:1)	40	10	
Blue NSB-339	Ultramarine Blue (P.Bl.29)	70	15	
Blue NSB-1/7-339-D	Ultramarine Blue (P.Bl.29)	10	15	
Green NSB-281	Phthalocyanine Green (P.G.7)	40	10	
Green NSB-1/10-281-D	Phthalocyanine Green (P.G.7)	4	10	
Violet NSB-603	Dioxazine Violet (P.V.37)	5	10	
Violet NSB-1/10-603-D	Dioxazine Violet (P.V.37)	0.5	5	
Black NSB-412	Carbon Black (P.Bk.7)	40	10	
Black NSB-414	Carbon Black (P.Bk.7)	36	10	
Black NSB-1/10-414-D	Carbon Black (P.Bk.7)	3.6	15	
Black NSB-1/100-414-Y	Carbon Black (P.Bk.7)	0.36	10	
Black NSB-422	Carbon Black (P.Bk.7)	4.7	15	
White NSB-513	Titanium Oxide (P.W.6)	72	15	
White NSB-524	Titanium Oxide (P.W.6)	72	15	

## Note

- Please mix the required amount into your PVC compound and check the color tone before use.
- If you are unsure about the amount of base color to add for your desired color tone, feel free to consult with us.
- Depending on the type of compound, there may be issues with pigment diffusion, external lubricity, or internal lubricity.

In such cases, please consult with us.

[Note]

Data on this page can't be used for specification purposes.  
Please evaluate the sufficient performance of the sample under the conditions of use.



RESINO COLOR INDUSTRY CO., LTD.

Head Office TEL: +81-6-6301-0636

Sales Office TEL: +81-3-3634-1746

<http://www.resinocolor.co.jp/>